

RECLAIMED WOOD

AH: Original, old wood with a surface full of character, sound and black knots possible, knotholes are filled with natural knot plugs, small unfilled parts possible, resin pockets possible, contrasting colour variations are a valued feature, worm holes, shakes, nail holes, mechanical damages, lamellas are jointfree placed.

Bottom layer AH: as above.

Bottom layer CG+: Spruce steamed, no special quality specifications, filled surface.

This panel is also available with a gluing adapted to wet areas (sauna) and is therefore in accordance with the emission requirements according to ONORM M6219-1:2010 for the use in sauna areas (see information "Admonter Element's in sauna areas" at <http://admonter.at/en/downloads/>).



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Grading	Thickness mm app.	Length mm (Width 2030 mm)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AH/CG+ (suitable for sauna use)	19	2100-5000 (subject to availability)	5	Mix	SML or BML Spruce (subject to availability)	30
AH/AH	19	2100-5000 (subject to availability)	5	Mix		30
AH/AH	42	2100/2500	5	Mix	Spruce 5-layer	10

Panels are glued SWP/2 NS (non structural): solid wood panels for non-structural use in wet areas, with regard to appropriate constructional protection also suitable for exterior use (sheltered areas).

Legend: SML = strip core, BML = board middle layer.

More information concerning fire classification in the accompanying information to CE-marking.

Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m²]	Moisture content [%]	Lambda [W/m K]
Reclaimed Wood	19	Spruce	8,9	8+/-2	0,12
	42	Spruce	19,7	8+/-2	0,12



You can find more detailed information at: admonter.at