

# GALLERIA - RECLAIMED WOOD ALDER GREY

Reclaimed wood from naturally weather-beaten alder with a surface full of character and colour variation; sound knots, black knots, knot holes and spike knots possible; pith ray, resin pockets, worm holes, shakes, nail holes, bark pockets and mechanical damages possible; colour variation caused by natural weathering of the wood is a valued feature. Top layers are joint free placed but not joint less glued. Longitudinal and transverse joints of top layers possible.

**Bottom layer:** Alder or softwood, no typical quality specification.



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Finish	Thickness mm app.	Width mm	Length mm	Top Layer thickness mm	Packaging pieces/package	Matching trim
untreated	19	244	1800/2100 2250	app. 7-9	4	25 x 60 mm

**up to 25 m<sup>2</sup> - length 2400 mm**  
**from 25 m<sup>2</sup> - Lengths are subject to availability**

GALLERIA **glued SWP/1 NS (non structural)**: solid wood panels for non-structural interior use.  
There is no risk of moisture penetration.

- Grooved on all four sides
- False tongue is included
- Matching trim and metal fixing brackets please see Admonter price list

More information concerning fire classification in the accompanying information to CE-marking.

## Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m <sup>2</sup> ]	Moisture content [%]	Lambda [W/m K]
Reclaimed Wood Alder grey	21	Spruce	10,5	7+/-2	0,13



You can find more detailed information at: [admonter.at](http://admonter.at)