

GALLERIA - RECLAIMED WOOD SUNBAKED BRUSHED

Reclaimed wood panel with a surface full of character and colour variation; heartwood, resin pockets, nail holes, treenails, spike knots, knots, black knots, bark pockets and worm holes acceptable; shakes, mechanical damages and blue stain conditionally acceptable, surface defects professionally filled (some are open); Colour range: mixed (grey, brown, black). Surface: raw / untreated, heavily brushed, the surface is naturally timeworn and weathered.

Top layers are joint free placed but not joint less glued.

Bottom layer C: Spruce, no special quality specification, not filled.



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Finish	Thickness mm app.	Width mm	Length mm	Top Layer thickness mm	Packaging pieces/package	Matching trim
brushed untreated	22	244	1800/2100/2250	approx. 7-10	4	25 x 60 mm

up to 25 m² - length 1800 mm
from 25 m² - Lengths are subject to availability

GALLERIA **glued SWP/1 NS (non structural)**: solid wood panels for non-structural interior use.
There is no risk of moisture penetration.


- Grooved on all four sides
- False tongue is included
- Matching trim and metal fixing brackets please see Admonter price list

More information concerning fire classification in the accompanying information to CE-marking.

Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.com/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m ²]	Moisture content [%]	Lambda [W/m K]
Reclaimed Wood sunbaked	19	Spruce	10,3	7+/-2	0,12



You can find more detailed information at: admonter.com