

111

Top layer approx. 3,6 mm

Maintenance oil natur

# TWIN OAK IGNIS lightly smoked

FLOOR<sup>S</sup>



## Admonter FLOORs on underfloor heating systems

Admonter FLOORs are ideally suited for underfloor heating systems. We recommend hot-water underfloor heating systems set at low temperature.

Please find detailed information in the information sheet Admonter FLOORs on underfloor heating systems!

#### Admonter accessories

The wide range of accessories matches the Admonter FLOORs and includes matching boarders, flush-mount skirting and solutions for staircases.

#### Regular care and maintenance

Please see the Admonter maintenance & installation instructions for small format floorboards.

### Further information

http://www.admonter.com/en/downloads/

| Grading  | Thickness<br>(mm) | Construction | Width<br>(mm) | Length (mm) |     | Texture          | Finish |  | Profile         |
|----------|-------------------|--------------|---------------|-------------|-----|------------------|--------|--|-----------------|
| noblesse | 15                | 3-Layer      | 120           | small       | 590 | sanded / brushed | ec     |  | Tongue & groove |
| basic    | 15                | 3-Layer      | 120           | small       | 590 | sanded / brushed | ec     |  | Tongue & groove |

Backing: Solid Wood / ec: natural oiled easy care / ml: matt lacquer

#### Please note:

Repair and supplementary oils can be found in the Admonter price list.

| Technical information  |                   |                   |                         |                |                    |                     |                     |  |  |  |  |  |
|--|-------------------|-------------------|-------------------------|----------------|--------------------|---------------------|---------------------|--|--|--|--|--|
| More information (for example concerning fire classification) in the accompanying information to CE-marking at http://www.admonter.com/en/downloads/ |                   |                   |                         |                |                    |                     |                     |  |  |  |  |  |
| Type of wood   | Thickness<br>(mm) | Weight<br>[kg/m²] | Moisture content<br>[%] | Lambda [W/m K] | d-Value R [m² K/W] | Hardness<br>[N/mm²] | Fire classification |  |  |  |  |  |
| Oak  | 10                | 5,7               | 7+/-2                   | 0,15           | 0,067              | 41                  | C <sub>f</sub> -s1  |  |  |  |  |  |
| Oak  | 15                | 8,6               | 7+/-2                   | 0,15           | 0,100              | 41                  | C <sub>ff</sub> -s1 |  |  |  |  |  |

